

PRODUCT:	SHRINKKOMP 20
TYPE:	FREE FLOW HIGH STRENGTH GROUT
NATURE OF BOND:	HYDRAULIC
INSTALLATION:	POURING

GENERAL PROPERTIES

Maximum Grain Size, mm	3
------------------------	---

PHYSICAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Water Required for Flowable Consistency, %	13 – 15	14.5	ASTM C 1107, ASTM C 1090 and ASTM C 1437
Compressive Strength, Kgs / cm²			BS EN 12390 – 1 to 4
24 hrs	100 – 220	200	
3 Days	280 – 350	340	
7 Days	380 – 450	430	
28 Days	500 – 550	540	
Linear Expansion, %			ACE test procedure TP/030 and ASTM C 806
Free	0.15 – 0.2	0.18	
Restrained	0.05 – 0.12	0.10	
% Retained Above Maximum Size	0 – 5	0.8	ASTM C 92

Packaging: 25 kg bags

Delivery State: Dry

Storage Life: Best till 6 months from the date of production, if stored in proper condition.

Note:

(1) The data are current production averages. They can not be used as limits for specification.